



TEST REPORT

Reference No. : SZ2022080685-1E

Date : Aug. 19, 2022

Page No.: 1 of 14

Client : Paul Stricker SA | Paul Stricker CZ s.r.o | Reda a.s.

Address : N.I. Murtede, It5 - 3060-372 Murtede – Portugal | Hviezdoslavova 55d, 627 00
Brno - Czech Republic

The following merchandise was (were) submitted and identified by the client as:

Name of Product : Ceramic Mug

Test Model : 94251 94253

Model May Cover : /

Main Material: /

Supplier: /

Buyer: /

Produced to : Paul Stricker SA


Manufacturer: 9810 - 0031669


Sample Received : Aug. 11, 2022

Test Period : Aug. 11, 2022 - Aug. 19, 2022

Test Specification and Conclusion:

Please refer to next page

Prepared By : 
David Chen
Testing Engineer

Reviewed By : 
Dora Cheng
Reporter Supervisor

Issued By : 
Ada Wang
Lab Manager



SZ2022080685-1E

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel.: +86/(0)512 67991866

Fax: +86/(0)512 87661802

Web: www.stq-cert.com

Technical service: TS@stq-cert.com

Customer service: CS@stq-cert.com

TEST REPORT

Reference No. : SZ2022080685-1E

Date : Aug. 19, 2022

Page No.: 2 of 14

Test Request		Conclusion
EU-European Commission Directive 1935/2004/EC relating to materials and articles intended to come into contact with foodstuffs		
1.	PCP content for wood	PASS
2.	Specific Migration of Extractable Formaldehyde for wood	PASS
3.	Specific Migration of Melamine for wood	PASS
European Council Directive 84/500/EEC and its amendment 2005/31/EC - Amending Council Directive 84/500/EEC as regards a declaration of compliance and performance criteria of the analytical method for ceramic articles intended to come into contact with foodstuffs, General Requirement (Article 3) in EU Regulation No. 1935/2004		
4.	Extractable Lead and Cadmium content for Ceramic	PASS
LFGB -German Food, Articles of Daily Use and Feed Code of September 1, 2005 (LFGB), Section 30 and 31 and BfR recommendation, General Requirement(Article 3) in EU Regulation No. 1935/2004		
5.	Sensorial examination odour and taste test for full article	PASS
DGCCRF -French Décret 92-631 and French recommendation DGCCRF 2004-64 and its amendment Décret no 2007-766 du 10 mai 2007, General Requirement (Article 3) in EU Regulation No. 1935/2004		
6.	Polychlorinated biphenyls (PCBs) Content for Wood	PASS
7.	Extractable Heavy Metals (Lead, Cadmium, Mercury) for Wood	PASS
8.	Organoleptic inertia for Wood	PASS
DGCCRF -French Décret 92-631 and French recommendation DGCCRF 2004-64 and its amendment Décret no 2007-766 du 10 mai 2007 and DM/4B/COM/002,General Requirement (Article 3) in EU Regulation No. 1935/2004		
9.	Leachable Lead, Cadmium, Aluminum, Cobalt and Arsenic content for Ceramic	PASS
Italy-Decree of the Ministry of Health of 4.4.85 (Italian official Gazette 26.4.85) and 84/500/EEC, General Requirement (Article 3) in EU Regulation No. 1935/2004		
Ministerial Decree of 21 March 1973 (Italy), General Requirement (Article 3) in EU Regulation No. 1935/2004, Guidelines for importation of material and articles intended to come into contact with food (MACF) from outside the EU(Version 12 30-10-2020)		
Serbia-O USLOVIMA U POGLEDU ZDRAVSTVENE ISPRAVNOSTI PREDMETA OPŠTE UPOTREBE KOJI SE MOGU STAVLJATI U PROMET		
10.	Sensorial examination odour and taste test for full article	PASS

***** To be continued *****

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhong Road, High-new district, Suzhou, China 215129

Tel.: +86/(0)512 67991866

Fax: +86/(0)512 87661802

Web: www.stq-cert.com

Technical service: TS@stq-cert.com

Customer service: CS@stq-cert.com

TEST REPORT

Reference No. : SZ2022080685-1E

Date : Aug. 19, 2022

Page No.: 3 of 14

TEST RESULTS:

1. Pentachlorophenol (PCP) Content

Test Method: With reference to §64 LFGB BVL B 82.02-8:2001-06.

Test Item	Unit	Result	Maximum Permissible Limit
		1#	
PCP Content	mg/kg	<0.05	0.15

2. Extractable Formaldehyde

Test Method: Sample preparation in 3% acetic acid at 70°C for 2 hours with reference to EN 13130-1: 2004; followed by analysis using UV-visible Spectrophotometer.

Surface area(dm²)/Volume(ml):1/167

Test Items	Unit	Result			Maximum Permissible Limit
		1#-1 st	1#-2 nd	1#-3 rd	
Extractable formaldehyde	mg/kg	< 3	< 3	< 3	15
conclusion*	---	PASS			---

3. Specific Migration of Melamine

Test Method: Sample preparation with reference to BS EN 13130-1:2004 with selection of simulants and condition, followed by analysis using High Performance Liquid Chromatography / Mass Spectrometer (HPLC/MS).

Surface area(dm²)/Volume(ml): 1/167

Test Items	Unit	Result			Maximum Permissible Limit
		1#-1 st	1#-2 nd	1#-3 rd	
Specific migration of Melamine in 3% acetic acid at 70°C, 2 hours	mg/kg	<2	<2	<2	2.5
conclusion*	---	PASS			---

TEST REPORT

Reference No. : SZ2022080685-1E

Date : Aug. 19, 2022

Page No.: 4 of 14

4. Extractable Lead and Cadmium Content

Test Method: As specified in EEC Directive 84/500/EEC and 2005/31/EC.

Analysis was performed by Atomic Absorption Spectrometer(AAS).

Sample No. :2#	Result				Category 2 Limit
	1	2	3	4	
Released Lead (mg/l)	< 0.1	< 0.1	< 0.1	< 0.1	4.0
Released Cadmium (mg/l)	< 0.01	< 0.01	< 0.01	< 0.01	0.3
Volume of 4% Acetic acid used (ml)	200	200	200	200	---
Depth (mm)	59	59	59	59	---
Diameter (mm)	78	78	78	78	---

Sample No. :3#	Result				Category 2 Limit
	1	2	3	4	
Released Lead (mg/l)	< 0.1	< 0.1	< 0.1	< 0.1	4.0
Released Cadmium (mg/l)	< 0.01	< 0.01	< 0.01	< 0.01	0.3
Volume of 4% Acetic acid used (ml)	200	200	200	200	---
Depth (mm)	59	59	59	59	---
Diameter (mm)	78	78	78	78	---

Sample No. :4#	Result				Category 2 Limit
	1	2	3	4	
Released Lead (mg/l)	< 0.1	< 0.1	< 0.1	< 0.1	4.0
Released Cadmium (mg/l)	< 0.01	< 0.01	< 0.01	< 0.01	0.3
Volume of 4% Acetic acid used (ml)	240	240	240	240	---
Depth (mm)	78	78	78	78	---
Diameter (mm)	68	68	68	68	---

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel.: +86/(0)512 67991866

Fax: +86/(0)512 87661802

Web: www.stq-cert.com

Technical service: TS@stq-cert.com

Customer service: CS@stq-cert.com

TEST REPORT

Reference No. : SZ2022080685-1E

Date : Aug. 19, 2022

Page No.: 5 of 14

Sample No. :5#	Result				Category 2 Limit
	1	2	3	4	
Released Lead (mg/l)	< 0.1	< 0.1	< 0.1	< 0.1	4.0
Released Cadmium (mg/l)	< 0.01	< 0.01	< 0.01	< 0.01	0.3
Volume of 4% Acetic acid used (ml)	240	240	240	240	---
Depth (mm)	78	78	78	78	---
Diameter (mm)	68	68	68	68	---

Sample No. :6#	Result				Category 2 Limit
	1	2	3	4	
Released Lead (mg/l)	< 0.1	< 0.1	< 0.1	< 0.1	4.0
Released Cadmium (mg/l)	< 0.01	< 0.01	< 0.01	< 0.01	0.3
Volume of 4% Acetic acid used (ml)	240	240	240	240	---
Depth (mm)	78	78	78	78	---
Diameter (mm)	68	68	68	68	---

Remark:

Category 1: Articles that cannot be filled and articles that can be filled, the internal depth of which does not exceed 25 mm.

Category 2: Articles, not in categories 1 or 3, which can be filled

Category 3: Cooking ware; packaging and storage vessels having a capacity of more than three liters

Lip and rim area for drinking utensils: With coating or colour within 20 mm along the lip and Rim area which is different from the colour of the interior cavity.

TEST REPORT

Reference No. : SZ2022080685-1E

Date : Aug. 19, 2022

Page No.: 6 of 14

5. Sensorial Examination Odour and Taste Test

Test Method: Sensory test with reference to DIN10955: 2004-06

Test procedure:

1. Wash the sample with distilled water and dry it at room temperature;
2. Total immersion by water and keep at 70°C for 2 hours;
3. Cool to room temperature;
4. Degust the taste and evaluate;
5. Test the Blank as the steps 1~4.

Test Items	Result	Maximum Permissible Limit
Sensorial examination odour (Point scale)	0	2.5
Sensorial examination taste (Point scale)	0	2.5

Scale evaluation:

- 0: No perceptible odour and taste
- 1: Odour and taste just perceptible (still difficult to define)
- 2: Moderate odour and taste
- 3: Moderately strong odour and taste
- 4: Strong odour and taste

6. Polychlorinated biphenyls (PCBs) Content

Test Method: With reference to EN ISO 15318:1999, Solvent extraction followed by analysis using GC/ECD.

Test Item(s)	Unit	Result(s)	Maximum Permissible Limit
		1#	
PCBs (Polychlorinated Biphenyls) (Including PCB18, PCB28, PCB52, PCB101, PCB153, PCB138 and PCB180)	mg/kg	<0.01	2

***** To be continued *****

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhong Road, High-new district, Suzhou, China 215129

Tel.: +86/(0)512 67991866

Fax: +86/(0)512 87661802

Web: www.stq-cert.com

Technical service: TS@stq-cert.com

Customer service: CS@stq-cert.com

TEST REPORT

Reference No. : SZ2022080685-1E

Date : Aug. 19, 2022

Page No.: 7 of 14

7. Extractable Heavy Metals(Lead, Cadmium & Mercury)

Test Method: Sample Preparation with reference to EN647:1993 (hot water extraction), followed by analysis using Inductively Coupled PlasmaOptical Emission Spectrometer.

Test Item(s)	Unit	Result(s)	Maximum Permissible Limit
		1#	
Extractable Lead	mg/kg	<0.1	3
Extractable Cadmium	mg/kg	<0.05	0.5
Extractable Mercury	mg/kg	<0.05	0.3

8. Organoleptic inertia

Test Method: With reference to NF ISO 13302:2004 Sensory Analysis - Methods for assessing modifications to the flavour of foodstuffs due to packaging.

Test Item(s)	Result(s)	Maximum Permissible Limit
	1#	
Organoleptic inertia	Absence of alteration in taste or smell of foods	Absence of alteration in taste or smell of foods

9. Leachable Lead, Cadmium, Aluminum, Cobalt and Arsenic Content

Test method: With reference to DM/4B/COM/002, Analysis was performed by Atomic Absorption Spectrometer.

Sample No. 2#:	Result				Category 2 Limit
	1	2	3	4	
Leachable Lead (mg/l)	< 0.1	< 0.1	< 0.1	< 0.1	4.0
Leachable Cadmium (mg/l)	< 0.01	< 0.01	< 0.01	< 0.01	0.3
Leachable Aluminum (mg/kg)*	< 0.01	< 0.01	< 0.01	< 0.01	1
Leachable Cobalt (mg/kg)*	< 0.01	< 0.01	< 0.01	< 0.01	0.02
Leachable Arsenic (mg/kg)*	<0.002	<0.002	<0.002	<0.002	0.002
Volume of 4% Acetic acid used (ml)	200	200	200	200	---
Depth (mm)	59	59	59	59	---
Diameter (mm)	78	78	78	78	---

Note: *Report the third extractive results.

TEST REPORT

Reference No. : SZ2022080685-1E

Date : Aug. 19, 2022

Page No.: 8 of 14

Sample No. 3#:	Result				Category 2 Limit
	1	2	3	4	
Leachable Lead (mg/l)	< 0.1	< 0.1	< 0.1	< 0.1	4.0
Leachable Cadmium (mg/l)	< 0.01	< 0.01	< 0.01	< 0.01	0.3
Leachable Aluminum (mg/kg)*	< 0.01	< 0.01	< 0.01	< 0.01	1
Leachable Cobalt (mg/kg)*	< 0.01	< 0.01	< 0.01	< 0.01	0.02
Leachable Arsenic (mg/kg)*	<0.002	<0.002	<0.002	<0.002	0.002
Volume of 4% Acetic acid used (ml)	200	200	200	200	---
Depth (mm)	59	59	59	59	---
Diameter (mm)	78	78	78	78	---

Note: *Report the third extractive results.

Sample No. 4#:	Result				Category 2 Limit
	1	2	3	4	
Leachable Lead (mg/l)	< 0.1	< 0.1	< 0.1	< 0.1	4.0
Leachable Cadmium (mg/l)	< 0.01	< 0.01	< 0.01	< 0.01	0.3
Leachable Aluminum (mg/kg)*	< 0.01	< 0.01	< 0.01	< 0.01	1
Leachable Cobalt (mg/kg)*	< 0.01	< 0.01	< 0.01	< 0.01	0.02
Leachable Arsenic (mg/kg)*	<0.002	<0.002	<0.002	<0.002	0.002
Volume of 4% Acetic acid used (ml)	240	240	240	240	---
Depth (mm)	78	78	78	78	---
Diameter (mm)	68	68	68	68	---

Note: *Report the third extractive results.

***** To be continued *****

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel.: +86/(0)512 67991866

Fax: +86/(0)512 87661802

Web: www.stq-cert.com

Technical service: TS@stq-cert.com

Customer service: CS@stq-cert.com

TEST REPORT

Reference No. : SZ2022080685-1E

Date : Aug. 19, 2022

Page No.: 9 of 14

Sample No. 5#:	Result				Category 2 Limit
	1	2	3	4	
Leachable Lead (mg/l)	< 0.1	< 0.1	< 0.1	< 0.1	4.0
Leachable Cadmium (mg/l)	< 0.01	< 0.01	< 0.01	< 0.01	0.3
Leachable Aluminum (mg/kg)*	< 0.01	< 0.01	< 0.01	< 0.01	1
Leachable Cobalt (mg/kg)*	< 0.01	< 0.01	< 0.01	< 0.01	0.02
Leachable Arsenic (mg/kg)*	<0.002	<0.002	<0.002	<0.002	0.002
Volume of 4% Acetic acid used (ml)	240	240	240	240	---
Depth (mm)	78	78	78	78	---
Diameter (mm)	68	68	68	68	---

Note: *Report the third extractive results.

Sample No. 6#:	Result				Category 2 Limit
	1	2	3	4	
Leachable Lead (mg/l)	< 0.1	< 0.1	< 0.1	< 0.1	4.0
Leachable Cadmium (mg/l)	< 0.01	< 0.01	< 0.01	< 0.01	0.3
Leachable Aluminum (mg/kg)*	< 0.01	< 0.01	< 0.01	< 0.01	1
Leachable Cobalt (mg/kg)*	< 0.01	< 0.01	< 0.01	< 0.01	0.02
Leachable Arsenic (mg/kg)*	<0.002	<0.002	<0.002	<0.002	0.002
Volume of 4% Acetic acid used (ml)	240	240	240	240	---
Depth (mm)	78	78	78	78	---
Diameter (mm)	68	68	68	68	---

Note: *Report the third extractive results.

Remark: Definition For ceramic wares according to French recommendation DGCCRF 2004-64:
Category 1: Articles that cannot be filled and articles that can be filled, the internal depth of which does not exceed 25 mm.
Category 2: Articles, not in categories 1 or 3, which can be filled
Category 3: Cooking ware; packaging and storage vessels having a capacity of more than three liters
Lip and rim area for drinking utensils: With coating or colour within 20 mm along the lip and Rim area which is different from the colour of the interior cavity.

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel.: +86/(0)512 67991866

Fax: +86/(0)512 87661802

Web: www.stq-cert.com

Technical service: TS@stq-cert.com

Customer service: CS@stq-cert.com

TEST REPORT

Reference No. : SZ2022080685-1E

Date : Aug. 19, 2022

Page No.: 10 of 14

10. Sensorial Examination Odour and Taste Test

Test Method: Sensory test with reference to DIN10955: 2004-06

Test procedure:

1. Wash the sample with distilled water and dry it at room temperature;
2. Total immersion by water and keep at 70°C for 2 hours;
3. Cool to room temperature;
4. Degust the taste and evaluate;
5. Test the Blank as the steps 1~4.

Test Items	Result	Maximum Permissible Limit
	1#	
Sensorial examination odour (Point scale)	0	2.5
Sensorial examination taste (Point scale)	0	2.5

Scale evaluation:

- 0: No perceptible odour and taste
- 1: Odour and taste just perceptible (still difficult to define)
- 2: Moderate odour and taste
- 3: Moderately strong odour and taste
- 4: Strong odour and taste

Test Part Description:

1# Bamboo cover

3# White ceramic mug

5# Grey ceramic mug

2# Black ceramic mug

4# Blue ceramic mug

6# White ceramic mug

SAMPLE PHOTOS



1#



2#

TEST REPORT

Reference No. : SZ2022080685-1E

Date : Aug. 19, 2022

Page No.: 11 of 14



3#



4#



5#



6#

***** To be continued *****

TEST REPORT

Reference No. : SZ2022080685-1E

Date : Aug. 19, 2022

Page No.: 12 of 14

PRODUCT PHOTO



***** END OF REPORT *****



TEST REPORT

Reference No. : SZ2022080685-1E

Date : Aug. 19, 2022

Page No.: 13 of 14

GENERAL CONDITIONS OF SERVICES

STQ Testing Services Co.,Ltd. (hereinafter "STQ"), The testing or examining under the request of the customer should obey terms as follow, according to regulation of "Contract Law of the People's Republic of China" on processing and undertaking contract, our company have legal right of termination without any reason and have the right to accept or refuse testing or examining request:

1. STQ only acts for the person or body originating the instructions (the "Clients"). No other party is entitled to give instructions, particularly on the scope of testing or delivery of report or certificate, unless authorized by the Clients.
2. Sample recycling: when the testing or examining is finished, the customer should recycle the sample. Within 30 days after issuing of testing report, if the customer could not recycle the sample or send notification of sample recycling in written (for example, if the sample belongs to consumables, toxic drugs, dangerous goods and other items that are not suitable for long-term storage, such as semi-finished products and fragile samples such as liquids and powders, the retention period will be shortened to 7 days). After the retention period, STQ has the right to dispose of the sample arbitrarily without paying compensation or compensation to the customer and take no responsibility for the consequences that damages the customer's trade secrets and intellectual property rights due to the loss of the sample.
3. The delivery and return fee of the samples which need to do testing at STQ should be paid by the client. STQ will not bear the responsibility for the testing error that is caused by transporting, packaging and labelling.
4. The Clients shall always comply with the following before or during STQ providing its services:
 - a) provide sample(s) and relevant data, at the same time, guarantee the consistence of the sample(s)' name they declared with the sample(s) or the goods provided. Otherwise, STQ will not bear any relevant responsibilities;
 - b) giving timely instructions and adequate information to enable STQ to perform the services effectively;
 - c) supply, when requested by STQ, any equipment and personnel for the performance of the services;
 - d) take all necessary steps to eliminate or remedy any obstruction in the performance of the services;
 - e) inform STQ in advance of any hazards or dangers, actual or potential, associated with any order of samples or testing;
 - f) provide all necessary access for STQ's representative to enable the required services to be performed effectively;
 - g) ensure all essential steps are taken for safety of working conditions, sites and installations during the performance of services;
 - h) fully discharge all its liabilities under any contract like sales contract with a third party, whether or not a report or certificate has been issued by STQ, failing which STQ shall be under no obligation to the Clients.
5. Subject to STQ's accepting the Client's instructions, STQ will issue reports or certificates which reflect statements of opinion made with due care within the scope of instructions but STQ is not obliged to report upon any facts outside the instructions, if there were any dissidence about the report or certificate, the Client should provide the written declaration to STQ within 15 days after the date receiving the report or certificate, otherwise, STQ will not hear the case after the date limit.
6. STQ is irrevocably authorized by the Clients to deliver at its discretion the report or the certificate to any third party when instructed by the Clients or where it implicitly follows from circumstances, trade custom, usage or practice as determined by STQ.
7. A test report will be issued in confidence to the Clients and it will be strictly treated as such by STQ. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of STQ. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by STQ, to his customer, supplier or other persons directly concerned. STQ will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the report unless required by the relevant governmental authorities, laws or court orders.
8. Applicants wishing to use STQ's reports in court proceedings or arbitration shall inform STQ to that effect prior to submitting the sample for testing.
9. The report will refer only to the sample tested and will not apply to the bulk, unless the sampling has been carried out by STQ and is stated as such in the Report. Also, the report is only for reference.
10. Any documents containing engagements between the Clients and third parties like contracts of sale, letters of credit, bills of lading, etc. are regarded as information for STQ only and do not affect the scope of the services or the obligations accepted by STQ.
11. If the Clients do not specify the methods/standards to be applied, STQ will choose the appropriate ones and further information regarding the methods can be obtained by direct contact with STQ, for the in-house method, STQ will only provide the summary.
12. No liability shall be incurred by and no claim shall be made against STQ or its servants, agents, employees or independent contractors in respect of any loss or damage to any such materials, equipment and property occurring whilst at STQ or any work places in which the testing is carried out, or in the course of transit to or from STQ or the said work places, whether or not resulting from any acts, neglect or default on the part of any such servants, agents, employees or independent contractors of STQ.
13. STQ will not be liable, or accept responsibility for any loss or damage howsoever arising from the use of information contained in any of its reports or in any communication whatsoever about its said tests or investigations.
14. Except for term 11 and term 12, if the test sample is damaged due to the negligence of ZOTAC, the total compensation for loss and damage to the sample or loss to the customer shall not exceed twice of the test service fee.
15. In the event of STQ prevented by any cause outside STQ's control from performing any service for which an order has been given or an agreement made, the Clients shall pay to STQ:
 - a) the amount of all abortive expenditure actually made or incurred;
 - b) a proportion of the agreed fee or commission equal to the proportion (if any) of the service actually carried out by STQ, and STQ shall be relieved of all responsibility whatsoever for the partial or total non-performance of the required service.

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhur Road, High-new district, Suzhou, China 215129

Tel.: +86/(0)512 67991866

Fax: +86/(0)512 87661802

Web: www.stq-cert.com

Technical service: TS@stq-cert.com

Customer service: CS@stq-cert.com



TEST REPORT

Reference No. : SZ2022080685-1E

Date : Aug. 19, 2022

Page No.: 14 of 14

16. STQ shall be discharged from all liabilities for all claims for loss, damage or expense unless suit is brought within one calendar year after the date of the performance by STQ of the service relating to the claim or in the event of any alleged non—performance within one year of the date when such service should have been completed.
17. The Clients acknowledge that STQ does not, either by entering into a contract or by performing service, assume or undertake to discharge any duty of the Clients to any other persons. STQ is neither an insurer nor a guarantor and disclaims all liability in such capacity.
18. The Clients shall hold harmless and indemnify STQ and its officers, employees, agents or independent contractors against all claims made by any third party for loss, damage or expense of whatsoever nature including reasonable legal expenses relating to the performance or non- performance of any services to the extent that the aggregate of any such claims relating to any one service exceed the limits mentioned in Clause 13.
19. Any unauthorized alteration, forgery or falsification of the content or appearance of the report/certificate is unlawful and offenders may be prosecuted to the fullest extent of the law; in the event of improper use of the report, STQ reserves the right to withdraw it, and to adopt any other measures which may be appropriate.
20. Samples are deposited with and accepted by STQ on the basis that either they are insured by the Clients or the Clients assumes entire responsibility for loss through fire, theft, burglary or for damages arising in the course of analysis or handling, without recourse whatsoever to STQ or its servants, agent, employees or independent contractors.
21. If the requirements of the Clients require the analysis of samples by the Clients' or any third party's laboratory, STQ will only convey the result of the analysis without responsibility for its accuracy. If STQ is only able to witness an analysis by the Clients' or any third Party's laboratory STQ will only confirm that the correct sample has been analyzed without responsibility for the accuracy of any analysis or results.
22. In the event of any unforeseen additional time or costs being incurred in the course of carrying out any of its services, STQ shall be entitled to charge the Clients additional fees to reflect the additional time and costs incurred.
23. All rights (including but not limited to copyright) in any reports, certificates or other materials produced by STQ in the course of providing its services shall remain vested in STQ.
24. Unless otherwise agreed in written, payment should be arranged within 10 days after the invoice date or the debit note date. If the payment is overdue, the overdue penalty shall be calculated at 1% per day of the unpaid part till the actual payment date. All expenses, costs and losses incurred by STQ as a result of collecting or claiming the fees owed shall be borne by the customer, including but not limited to attorney fees, litigation fees, preservation fees, preservation guarantee fees, travel expenses, etc.
25. Test results may be transmitted by electronic means at the Client's request. However, it should be noted that electronic transmission cannot guarantee the information contained will not be lost, delayed or intercepted by third party. STQ is not liable for any disclosure, error or omission in the content of such messages as a result of electronic transmission.
26. If necessary, STQ may subcontract part of or all tests to competent subcontractors. If no objection is raised at the time of the Clients submitting the application, STQ shall assume the Client's approval.
27. This report/certificate does not relieve sellers/suppliers from their contractual responsibility with regards to the quality/quantity of this delivery nor does it prejudice the Client's right to claim towards sellers/suppliers for compensation for any apparent and/or hidden defects not detected during STQ's random inspection or testing or audit.
28. The testing data and result(s) in this reportis(are) just for scientific research, education, internal quality control and product development etc.
29. STQ reserves the right to include Special Conditions in addition to the foregoing General Conditions if warranted by the particular circumstances of the required test or investigation [this clause is only effective when the other party has been informed].
30. The foregoing General Conditions shall in all respects be governed, construed, interpreted and operated in accordance with the relevant Chinese laws and regulations. Unless otherwise agreed, the arbitration shall take place in P. R. C
31. These General Condition have been drafted in Chinese and may be translated into other languages. In the event of any discrepancy, the Chinese version shall prevail.
32. In general sample will be stored for 30 days. But for liquid, powder, etc semi-product & fragile product, it will be stored only for 7 days.

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel.: +86/(0)512 67991866

Fax: +86/(0)512 87661802

Web: www.stq-cert.com

Technical service: TS@stq-cert.com

Customer service: CS@stq-cert.com